

# 10oz ECONOMY FRONTLIT

## Fire Certificate

REPORT # : H216-09-17509-01  
 SAMPLE RECEIVED DATE : 04-10-2009  
 TEST STARTED DATE : 04-10-2009  
 REPORT ISSUED DATE : 04-30-2009



**TEST CONDUCTED: FLAMMABILITY { NFPA 701 TEST METHOD 1 (2004)}**

TEST RESULT:

SAMPLE NUMBER	WEIGHT (g)		WEIGHT LOSS (%)	AFTER FLAME TIME (s)	DRIP BURNS (s)
	ORIGINAL	AFTER			
1	33.4	29.4	12.0	0.0	0.0
2	33.7	28.9	14.2	0.0	0.0
3	33.5	29.3	12.5	0.0	0.0
4	33.4	29.2	12.6	0.0	0.0
5	33.6	28.8	14.3	0.0	0.0
6	33.6	28.8	14.3	0.0	0.0
7	33.6	28.9	14.0	0.0	0.0
8	33.7	28.3	16.0	0.0	0.0
9	33.4	29.1	12.9	0.0	0.0
10	33.6	29.0	13.7	0.0	0.0
<b>AVG</b>	<b>33.6</b>	<b>28.3</b>	<b>15.2</b>	<b>0.0</b>	<b>0.0</b>

Note - Conclusion: Based upon the results of the test report, the submitted sample meets the performance requirement as stated in NFPA 701 TEST METHOD 1 (2004).

PERFORMANCE CRITERIA FOR TEST 1:

<b>DRIP BURN(S)</b>	<b>WEIGHT LOSS (%)</b>	NO INDIVIDUAL SPECIMEN'S WEIGHT LOSS EXCEED THE MEAN VALUE PLUS 3 STANDARD DEVIATION 17.2 (STANDARD DEVIATION = 1.19)
<b>AVG: LESS THAN 2</b>	<b>AVG: LESS THAN 40</b>	

TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENTS REQUEST.