

11oz ECONOMY FRONTLIT FOR TURBOJET Fire Certificate

REPORT # : H216-09-16952-01
 SAMPLE RECEIVED DATE : 04-06-2009
 TEST STARTED DATE : 04-06-2009
 REPORT ISSUED DATE : 04-29-2009



TEST CONDUCTED: FLAMMABILITY { NFPA 701 TEST METHOD 1 (2004)}

TEST RESULT:

SAMPLE NUMBER	WEIGHT (g)		WEIGHT LOSS (%)	AFTER FLAME TIME (s)	DRIP BURNS (s)
	ORIGINAL	AFTER			
1	27.1	22.8	15.9	0.0	0.0
2	27.8	24.2	12.9	0.0	0.0
3	27.1	21.6	20.3	0.0	0.0
4	27.4	22.0	19.7	0.0	0.0
5	27.6	23.9	13.4	0.0	0.0
6	27.1	21.6	20.3	0.0	0.0
7	27.6	21.6	21.7	0.0	0.0
8	27.5	23.5	14.5	0.0	0.0
9	27.6	23.9	13.4	0.0	0.0
10	27.5	24.1	12.4	0.0	0.0
AVG	27.4	23.1	15.7	0.0	0.0

Note - Conclusion: Based upon the results of the test report, the submitted sample meets the performance requirement as stated in NFPA 701 TEST METHOD 1 (2004).

PERFORMANCE CRITERIA FOR TEST 1:

DRIP BURN(S)	WEIGHT LOSS (%)	NO INDIVIDUAL SPECIMEN'S WEIGHT LOSS EXCEED THE MEAN VALUE PLUS 3 STANDARD DEVIATION 26.6 (STANDARD DEVIATION = 3.62)
AVG: LESS THAN 2	AVG: LESS THAN 40	

TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENTS REQUEST.