

13oz ECONOMY FRONTLIT

Fire Certificate

REPORT # : H216-08-02762-01
 SAMPLE RECEIVED DATE : 05-15-2008
 TEST STARTED DATE : 05-05-2008
 REPORT ISSUED DATE : 05-21-2008



TEST CONDUCTED: FLAMMABILITY { NFPA 701 TEST METHOD 1 (2004)}

TEST RESULT:

| SAMPLE NUMBER | WEIGHT (g) | | WEIGHT LOSS (%) | AFTER FLAME TIME (s) | DRIP BURNS (s) |
|---------------|-------------|-------------|-----------------|----------------------|----------------|
| | ORIGINAL | AFTER | | | |
| 1 | 27.1 | 23.1 | 14.8 | 0.0 | 0.0 |
| 2 | 27.6 | 21.6 | 21.7 | 0.0 | 0.0 |
| 3 | 27.5 | 23.5 | 14.5 | 0.0 | 0.0 |
| 4 | 27.6 | 23.9 | 13.4 | 0.0 | 0.0 |
| 5 | 27.1 | 22.8 | 15.9 | 0.0 | 0.0 |
| 6 | 27.8 | 24.2 | 12.9 | 0.0 | 0.0 |
| 7 | 27 | 23.9 | 11.5 | 0.0 | 0.0 |
| 8 | 27.1 | 21.6 | 20.3 | 0.0 | 0.0 |
| 9 | 27.4 | 22.0 | 19.7 | 0.0 | 0.0 |
| 10 | 27.5 | 24.1 | 12.4 | 0.0 | 0.0 |
| | | | | | |
| AVG | 27.4 | 23.1 | 15.7 | 0.0 | 0.0 |

Note - Conclusion: Based upon the results of the test report, the submitted sample meets the performance requirement as stated in NFPA 701 TEST METHOD 1 (2004).

PERFORMANCE CRITERIA FOR TEST 1:

| | | |
|-------------------------|--------------------------|---|
| DRIP BURN(S) | WEIGHT LOSS (%) | NO INDIVIDUAL SPECIMEN'S WEIGHT LOSS EXCEED THE MEAN VALUE PLUS 3 STANDARD DEVIATION 26.6 (STANDARD DEVIATION = 3.62) |
| AVG: LESS THAN 2 | AVG: LESS THAN 40 | |

TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENTS REQUEST.