

8oz PREMIUM MESH W/ LINER

Fire Certificate

REPORT # : H216-08-02762
 SAMPLE RECEIVED DATE : 05-15-2008
 TEST STARTED DATE : 05-15-2008
 REPORT ISSUED DATE : 05-21-2008



TEST CONDUCTED: FLAMMABILITY { NFPA 701 TEST METHOD 1 (2004) }

TEST RESULT:

SAMPLE NUMBER	WEIGHT (g)		WEIGHT LOSS (%)	AFTER FLAME TIME (s)	DRIP BURNS (s)
	ORIGINAL	AFTER			
1	17.5	12.6	28.0	0.0	0.0
2	17.5	13.4	23.4	0.0	0.0
3	17.6	12.7	27.8	0.0	0.0
4	17.4	12.8	26.4	0.0	0.0
5	17.4	13.1	24.7	0.0	0.0
6	17.6	13.0	26.1	0.0	0.0
7	17.2	12.1	29.8	0.0	0.0
8	17.4	12.6	27.6	0.0	0.0
9	17.5	12.8	26.9	0.0	0.0
10	17.4	12.9	25.9	0.0	0.0
AVG	17.5	12.8	26.7	0.0	0.0

Note - Conclusion: Based upon the results of the test report, the submitted sample meets the performance requirement as stated in NFPA 701 TEST METHOD 1 (2004).

PERFORMANCE CRITERIA FOR TEST 1:

DRIP BURN(S)	WEIGHT LOSS (%)	NO INDIVIDUAL SPECIMEN'S WEIGHT LOSS EXCEED THE MEAN VALUE PLUS 3 STANDARD DEVIATION 32.0 (STANDARD DEVIATION = 1.79)
AVG: LESS THAN 2	AVG: LESS THAN 40	

TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENTS REQUEST.